


Longpass / UV Transmitting | 9345



OPTICAL PROPERTIES

Wavelength (nm)	345	400	
Internal Transmittance	≥ 0.50	≥ 0.85	

PHYSICAL PROPERTIES

Nominal Thickness Range	2.0 mm
Refractive Index	1.51
Density	2.41 g/cm ³
Linear Thermal Expansion	52 E ⁻⁷ C ⁻¹ (30-300°C)
Strain Temperature	531 °C
Annealing Temperature	545 °C
Deformation Temperature	620 °C